

Description

3-mil, rigid, translucent blue PVC film with a matte surface formulated for use in stencil applications.

Release Liner

84# silicone-coated paper

Adhesive

Clear, water-based, low-tack removable adhesive

Area of Use

Developed for use in paint and stain stencil applications, especially for paint and spray techniques on smooth, flat, rigid substrates and surfaces. Applications requiring transparency of the paint mask for substrate visibility.

Great for gymnasium floor paint and stain mask, as well as hobby and craft applications, such as painted drywall, cabinets, custom bag-toss game boards, and wooden home décor signage.

Technical Tips

- Not suitable for wet applications.
- Remove the stencil film prior to baking, for those liquid paints that require baking to chemically cure.
- Users should always test their painting process to ensure stencil films are compatible.
 - Stencil films may leave adhesive residue behind if left on a freshly painted or porous surface for too long.

Technical Data

Thickness (without liner and adhesive)	3-mil
Dimensional Stability (FINAT TM-14)	Adhered to steel, no shrinkage in cross direction; In length, <.016"
Fire Behavior (DIN 75200) Fire Rating	Adhered to steel, self-extinguishing ASTM E 84-07 Class "A"
Adhesive Power (FINAT TM-1, after 24 h, average)	Adhered to stainless steel: 1.37 lb/in
Tensile Strength (DIN EN ISO 527)	Along: Min. 19 MPa Across: Min. 19 MPa
Elongation at Break (DIN EN ISO 527)	Along: Min. 90% Across: Min. 90%
Shelf Life (68°F/50% relative humidity)	2 years
Minimum Application Temperature	50°F
Available Lengths Available Widths	150' (50 yard) 15" (punched), 24", 30", 36", 48"
Recommended Application Tapes	ORATAPE® HT55, MT95, MT72, MT80P



ORAFOL Americas – GA
1100 Oracal Parkway
Black Creek, GA 31308
Phone: 888.672.2251

ORAFOL Americas – CT
120 Darling Drive
Avon, CT 06001
Phone: 800.654.7570

ORAFOL Canada
2831 Bristol Circle
Oakville, Ontario L6H 6X5
Phone: 888.727.3374

techsupport-americas@orafol.com – www.orafol.com

Note

Surfaces to which the material will be applied must be thoroughly cleaned from dust, grease or any contamination which could affect the adhesion of the material. Freshly lacquered or painted surfaces should be completely cured. The compatibility of selected lacquers and paints should be tested by the user, prior to application of the material. Films with structured surface are naturally more sensitive than the unstructured. Accordingly, these films are to be treated carefully both in processing and in cleaning. Impurities affect the appearance of structured films and require more frequent cleaning. Furthermore the application information published by ORAFOL is to be considered. The batch traceability according to ISO 9001 is possible on the basis of the roll number.

IMPORTANT NOTICE

All ORAMASK® products are subject to careful quality control throughout the manufacturing process and are warranted to be of merchantable quality and free from manufacturing defects. Published information concerning ORAMASK® products is based upon research which the Company believes to be reliable although such information does not constitute a warranty. Because of the variety of uses of ORAMASK® products and the continuing development of new applications, the purchaser should carefully consider the suitability and performance of the product for each intended use, and the purchaser shall assume all risks regarding such use. All specifications are subject to change without prior notice.

WARNING: This product contains chemicals known to the State of California to cause cancer, birth defects or other reproductive harm.



ORAFOL Americas – GA
1100 Oracal Parkway
Black Creek, GA 31308
Phone: 888.672.2251

ORAFOL Americas – CT
120 Darling Drive
Avon, CT 06001
Phone: 800.654.7570

ORAFOL Canada
2831 Bristol Circle
Oakville, Ontario L6H 6X5
Phone: 888.727.3374

techsupport-americas@orafol.com – www.orafol.com